

Abstract of the Disclosure

A powder coating composition comprises a mixture, in particulate form, of a zeolite and an organic resin, said zeolite containing less than 9 per cent water by weight as determined by heating at 800°C for 1 hour. The zeolite can act as an extender for titanium dioxide in systems containing the latter.